



Reclaimed Materials

Material : Cubic Zirconia Fines

Quality

Chemical

ZrO2 (HfO2)	:	71.50 %
Y2O3	:	17.00 %
Al2O3	:	0.30 %
Fe2O3	:	0.30 %
CaO	:	0.30 %
Others (each)	:	<0.05 %

Physical

Moisture content	:	20.00 %
Particle Size		
D50	:	6um
D90	:	25um

Availability

5-10mts a month

Please contact us for further details

ZIRCOMET Ltd, 16-20 Regent Street, Cambridge CB2 1DB, England

Tel : +44 (0)1223 967590 / Fax : +44 (0)1223 967591 / enquiries@zircomet.com

www.zircomet.com