

Zirconium Hydroxides for Catalysis



Zirconium Hydroxide

Grade	d50(um)	BET SA (m2/g)	LOI(%)	SO3(%)	WO3(%)	pH
TZH-85H	20-25	>300	15-20	<0.05	<0.05	-
TZH-85M	1-5	>300	15-20	<0.05	<0.05	-

Sulphated Zirconium Hydroxide

Grade	d50(um)	BET SA (m2/g)	LOI(%)	SO3(%)	WO3(%)	pH
TZH-85H-SO3	20-25	>200	25-35	10-11	<0.05	2-3
TZH-85M-SO3	1-5	>200	25-35	10-11	<0.05	2-3

Tungstated Zirconium Hydroxide

Grade	d50(um)	BET SA (m2/g)	LOI(%)	SO3(%)	WO3(%)	pH
TZH-85-WO3	20-25	>200	15-25	<0.05	15-16	-
TZH-85M-WO3	1-5	>200	15-25	<0.05	15-16	-